



MONIER ROOFCOAT

1/2

Monier Roofcoat is a water based 100% acrylic polymer high gloss colour coating for application over concrete roof tiles. Typical tile examples where Monier Roofcoat would be used are: Monier, Boral, Bristle Gregson, Standards, Bungalows and some Atlas tiles depending on surface roughness. If the tiles are very rough, Monier Roofcoat Primer or High-Build Primer is recommended to fill in and smooth badly worn tiles. Monier Roofcoat is also an excellent high gloss coloured top coat for most metal roofs which have previously been treated with Monier Roofcoat Primer.

Uses

- Monier Roofcoat is a high gloss 100% acrylic water based top coat designed to beautify most types of roofing surfaces. It can be used on concrete roof tiles and most metal roofs previously treated with Monier Roofcoat Primer. Monier Roofcoat is **not** recommended for Terracotta roof tiles or concrete driveways.

Features/Advantages

- Provides excellent adhesion to most primed or sealed roofing surfaces
- Ideal for recoating weathered roofs and roof repairs
- Colour matched to all commercially available roof tiles
- Under normal weather conditions Roofcoat can be recoated in 2 hours
- Water cleanup.



Instructions for Use/Application Instructions

- In order to provide the best result, it is important to understand the basic film forming process of the coatings and the problems that may arise.
- All coatings contain water and a solvent which keeps the polymer particles soft. This solvent is called a coalescing solvent or coalescent. Ideally, as the coating starts to dry, the water and coalescent release from the coating and the soft polymer particles are forced into each other. The process is called coalescence and proper coalescence of the coating film is vital if high gloss, adhesion, and long term durability is to be obtained. When the process of coalescence is fully completed, the coating film is said to be cured. This may take a week from the time of application to occur. The primer is an exception. It penetrates into the cement tile and gains adhesion by forming a physical bond, not chemical, with the tile. The following coat will then chemically bond with the primer. Some tiles however become almost non-porous during the manufacturing process and it is necessary treat them like metal surfaces. With these tiles and metal surfaces, it is necessary for the primer to "key" to the surface by forming a chemical bond. It takes about 24 hours to ensure maximum adhesion occurs, before the next coat is applied.
- There are many factors which can affect the film forming process. Dry time, temperature, humidity, film thickness, number of coats applied, number of coats in one day and wind are the most common.
- Thoroughly clean concrete roof tiles with high pressure water blaster to remove any dirt, moss or any other loose material. Allow to dry before applying Monier Roofcoat primer or colour coating products.
- Apply Monier Roofcoat by airless spray, brush or roller going top-bottom, not across the roof.

Important Notes/Limitations

- Apply a minimum of 2 coats for maximum gloss and durability.
- Not recommended for application below 14°C or over 32°C air temperature. This is particularly important when coating metal roofs.
- As a general rule: "If the roof is too hot to touch, it is too hot to paint".
- In cold conditions the air temperature may be within our guidelines but the roof surface may be much colder. In this case, allow the surface to warm up before spraying, brushing or rolling.
- DRYING TIME: Allow 2 hours before applying the next coat. Drying time will be affected by the surface type and condition and the weather. High humidity, dew, rain etc will affect the drying process and should be taken into consideration before spraying.



MONIER ROOFCOAT

2/2

Safety

- Monier Roofcoat is classified as non-hazardous by work safe Australia however as a general safety precaution:
- Avoid contact with skin and eyes.
- Keep out of reach of children.
- Use in well ventilated area. Wash hands after use.
- If eye contact: wash out with water.
- Seek medical assistance if irritation persists.
- If swallowed: drink plenty of water. Do not induce vomiting - Seek medical assistance.

Drinking Water

- Monier Roofcoat is suitable for roofs used to collect drinking water. If the roof is going to be used to collect drinking water, disconnect all downpipes attached to the water tank before spraying. After all coatings have been applied, wait for 2 good rainfalls before reconnecting the downpipes.

Coverage

For concrete tiles roofs:

- Primer: 80 square metres / 20 litre pail
- High-Build Primer: 70 square metres / 20 litre pail
- **Monier Roofcoat: 45 square metres / 10 litre pail**
- **Monier Roofcoat: 90 square metres / 20 litre pail**

For metal roofs:

- **Monier Roofcoat: 55 square metres / 10 litre pail**
- **Monier Roofcoat: 110 square metres / 20 litre pail**
- For best results we suggest 1 coat of Primer or High-Build Primer and 2 coats of Monier Roofcoat giving a total maximum dry film thickness of 0.2mm or 200 micron.

Clean up

Clean all equipment with water after use.

Product Disclaimer

The performance of this product is dependent on application procedures and conditions beyond our control. This makes it impossible for Monier to assume responsibility for any loss arising from the use of this product. Our liability will therefore be limited to the replacement of the product only. Monier also reserves the right to alter formulations specifications, application procedures and recommendations without notice.

Disclaimer

All information contained in this Product Information Sheet is as accurate and up-to-date as possible. Products can be expected to perform as indicated in this Sheet, so long as application procedures are followed as recommended. Notwithstanding the above, any recommendations made by Monier or its distributors in relation to this or other products is to be taken as advice only. Monier makes no representations or warranties that this product will be suitable for use. Subject to any applicable legislation which cannot be excluded (such as the Australian Consumer Law), Monier takes no responsibility and will not be liable for any failure in performance of this product or any losses, damages, or injuries (consequential or otherwise) arising from the storage, mixing, application or other use of this product or for any representations made by you about the product which have not been approved in writing by Monier. The buyer assumes all risk and responsibility for the use of this product.